

**PA66 8014L**

Glass Reinforced, Toughened, Nylon 66 resin.

Property	Test Method	Units	Value
			DAM
<b>Mechanical</b>			
Tensile Strength	ASTM D 638	psi	14,300
Elongation @ Break	ASTM D 638	%	4
Flexural Modulus	ASTM D 790	psi	660,000
Izod Impact	ASTM D256	ft lb/in	3.0
<b>Thermal</b>			
Heat Deflection Temperature	ASTM D 648	°F	365
1.8 Mpa (264 psi)	ASTM D 3418	°F	505
Melting Point			
<b>Other</b>			
Specific Gravity	ASTM D 792		1.19
<b>Processing</b>			
Melt Temperature Range		°F	540 - 560
Mold Temperature Range		°F	150-250
Processing Moisture Content		%	<0.20

Mechanical properties measured at 23°C (73°F)

Contact JEDA Polymers, LLC for MSDS, general guidelines and/or additional information about ventilation, handling, purging, drying, etc.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since JEDA Polymers cannot anticipate all variations in actual end-use conditions JEDA Polymers makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body.